



PROLASTIC MEGA UV 240

*Cement Acrylic Based
Dual Component UV Resistant
Super Flexible Waterproofing Product*

PRODUCT DESCRIPTION:

It is a two component, cement based, white colored fully elastic waterproofing mortar containing UV resistant polymer emulsion, containing special chemicals and resistant to light pedestrian traffic.

FEATURES:

It has high elasticity.
It is highly resistant to the negative effects of UV rays.
Crack bridging feature is at the highest level.
Its adherence is strong.
It adheres perfectly to mineral-based surfaces.
It is resistant to temperature differences.

PRODUCT INFORMATION:

Powder Component:

Chemical Base	Cement-based
Appearance / Color	Powder / white

Liquid Component:

Chemical Base	Acrylic based / Water based
Appearance / Color	Liquid / White
Dry Film Color	Transparent
Ph	5-7

PERFORMANCE:

(23°C, 50% RH)

Dry Bulk Density (powder component)	1650 ± 200 kg/m ³ TS EN 1015-10
Density (liquid component)	0.98-1.1 gr/cm ³
Crack bridging	≥ 1 mm TS EN 1062-7 (+23 °C)
Capillary water absorption	<0.1 kg/m ² .h0.5 TS EN 1062-3
Adhesion to Concrete	≥ 0.5 MPa TS EN 1542

These values have been obtained as a result of laboratory experiments and are valid for the performance of the finished applications at the end of the full drying period. Since the temperature and humidity values in the construction site environment and the application surfaces and areas will vary, the values may change.



PROLASTIC MEGA UV 240

*Cement Acrylic Based
Dual Component UV Resistant
Super Flexible Waterproofing Product*

USAGE AREAS:

In areas such as roofs and terraces that will remain open
On mineral surfaces such as concrete, plaster, screed as a surface
On balconies and terraces
On horizontal and vertical surfaces
It is used in waterproofing of structures above ground in waterproofing from the positive side.

APPLICATION INSTRUCTIONS:

Application surfaces should be damp, dry surfaces should be moistened before application. Surface; It should be cured and solid. It must be cleaned of residues such as oil, grease, dirt, paint, salt vomit that will prevent adhesion. PROREPAIR THIN or PROREPAIR if the surface is defective; If the application will be made in environments exposed to high sulphate such as sea water and sewage, it should be repaired with PROREPAIR PLUS at least 24 hours in advance. It is recommended to apply PROGEN PR before applying to very porous surfaces. It prevents salt vomit. Corners and joints should be turned with waterproofing bevel tape.

20 kg powder component is poured slowly into 10 kg liquid component and mixed with the help of low speed mixer until no lump remains. Absolutely no water should be added. Let the mortar rest for 3-5 minutes to mature. It is mixed again before starting the application.

Application Equipment:

Hand Mixer
Steel Trowel
Roller Brush

It is applied with a brush, trowel or suitable spray equipment. It should be applied to the surface in 2-3 layers. A waterproofing mesh should be applied between floors. The application of each layer should be done in a perpendicular direction to the previous one. Wait at least 24 hours between coats. The total layer thickness should be no more than 2-3 mm. Dusting of the intercoat surface should be prevented. For maximum benefit from the product, it is recommended to complete the process within 2-3 hours at most. It is not applied in places with traffic load. Expired mortar should be disposed of.



PROLASTIC MEGA UV 240

***Cement Acrylic Based
Dual Component UV Resistant
Super Flexible Waterproofing Product***

LIMITATIONS:

Please obey to the application instructions to obtain optimum quality. The application should be done between +5 C and +30 C. It should not be applied in very high temperature, direct exposure to sunlight, very windy, rainy weather. It should not be applied on surfaces where there is a danger of frost. The product should be protected from rain, water, frost and adverse external factors until it cures (28 days).

CONSUMPTION:

Approximately 2.5-3 kg/m² for 2 coats.

PACKAGING:

Liquid component: 10 kg bag drum

Powder component: in 20 kg kraft bag

SHELF LIFE:

It is 1 year from the date of production in its original packaging in dry and non-humid (temperature between +5 C and +25 C) environments. The lid of the containers should be tightly closed when not in use. It should be kept away from moisture.

STORAGE CONDITIONS:

It should be stored in its unopened original package, in a moisture-free, dry and cool (temperature between +5 C and +25 C) environment. It should not be left under direct sunlight.

SECURITY:

Since it is cement based, do not breathe the dust, use a mask. Avoid contact with skin and eyes. Use protective gloves, goggles and clothing. In case of eye contact, rinse with plenty of water and seek medical advice immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet.

DEKOSTAR San.ve Tic.Ltd. Şti. is not responsible for any application errors that may occur if the product is used for purposes other than its intended use or if the above-mentioned application conditions and recommendations are not followed. Dekostar reserves the right to change its products. Users should consider the latest edition of the Technical Data Sheet of the relevant product