



PROFUGA POOL 447

**Cement Based High Performance
Flexible Joint Filler Mortar CG2WA**

PRODUCT DESCRIPTION:

It is a cement-based, mold and fungus resistant, flexible joint filling material suitable for 1-6 mm joint gaps.

FEATURES:

- It is resistant to fungus and mold formation.
- It is resistant to water, moisture and impacts.
- It is water repellent.
- Suitable for 1-6 mm joint spacing.
- It has high adhesion strength.
- Its adherence is high.
- It provides a smooth surface.

PRODUCT INFORMATION:

Chemical Base	Cement-Based
Appearance / Color	Powder / Color Chart

PERFORMANCE:

(23°C, 50% RH)

Hollow Unit Volume Mass of Fresh Mortar 1350 ± 200 kg/m³ TS EN 1015-6

Grain Size Distribution

Amount remaining on the sieve with 1 mm opening	≤ 1.0% TS EN 1015-1
Compressive Strength 28 days	≥ 4.0 N/mm ² TS EN 1015-11
Flexural Strength 28 days	≥ 2.0 N/mm ² TS EN 1015-11
Water Absorption: (after 30 minutes)	≤ 5 gr TS EN 12808
Water Absorption: (After 240 minutes)	≤ 10 gr TS EN 12808

Pot life: 1 hour

These values have been obtained as a result of laboratory tests carried out in our company and are valid for the performance of the finished applications at the end of the full drying period. Since the temperature and humidity values in the construction site environment and the application surfaces and areas will vary, the values may change.



PROFUGA POOL 447

**Cement Based High Performance
Flexible Joint Filler Mortar CG2WA**

USAGE AREAS:

It is used for filling 1-6 mm joint gaps of coating materials such as ceramic, marble, natural stone, glass mosaic, indoors, on the floor and on the wall. It can be used safely in areas such as bathrooms, kitchens, balconies and terraces. Wet, such as pool, water tank, sauna, spa, bath. It gives excellent results in bulky spaces, in places with sudden heat transformations such as underfloor heating, in horizontal and vertical applications.

APPLICATION INSTRUCTIONS:

Joints should be dry and solid. The tile adhesive must be completely dry. It must be cleaned of residues such as oil, grease, dirt, paint, salt vomit that will prevent adhesion. In a hot and dry environment, the joints should be moistened with water before application.

Slowly pour 20 kg of PROFUGA POOL onto 4-4.5 lt of water and mix with the help of a low-speed mixer until no lumps remain. Adding more or less water than specified may cause cracking, dusting and color defects. Let the mortar rest for 5-10 minutes to mature. It is mixed again before starting the application.

Application Equipment:

Hand Mixer
Trowel
Filler Trowel
Sponge Cloth

Until the ceramics are adhered and dry, contact with water should be avoided. The prepared mortar should be spread on the surface, and the joint gaps should be filled with a rubber-sided filler trowel with cross movements and the excess should be scraped off from the surface. When the grouting material dries, the surface should be cleaned with a damp sponge with circular movements. Clean the application tools with water. Expired or crusted mortar in the container should be disposed of. After application, hands and application tools should be washed with plenty of water.

LIMITATIONS:

Please obey to the application instructions to obtain optimum quality. The application should be done between +5 C and +30 C. It should not be applied in hot, rainy and windy weather. It should not be applied on surfaces where there is a danger of frost. The product should be protected from rain, water, frost and adverse external factors until it cures (28 days).



PROFUGA POOL 447

**Cement Based High Performance
Flexible Joint Filler Mortar CG2WA**

CONSUMPTION:

It varies depending on the joint width and ceramic size.

PACKAGING:

In 20 kg kraft bags,

SHELF LIFE:

It is 1 year from the date of production in its original packaging in a humidity-free, dry and cool (temperature between +5 C and +25 C) environment. The lid of the containers should be tightly closed when not in use. It should be kept away from moisture.

STORAGE CONDITIONS:

It should be stored in its unopened original package, in a moisture-free, dry and cool (temperature between +5 C and +25 C) environment. It should not be left under direct sunlight.

SECURITY:

Since it is cement based, do not breathe the dust, do not contact the skin and eyes. Use mask. Use protective gloves, goggles and clothing. In case of eye contact, seek medical advice immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet.

DEKOSTAR San.ve Tic.Ltd. Şti. is not responsible for any application errors that may occur if the product is used for purposes other than its intended use or if the above-mentioned application conditions and recommendations are not followed. Dekostar reserves the right to change its products. Users should consider the latest edition of the Technical Data Sheet of the relevant product.

DEKOSTAR San. ve Tic. Ltd. Şti
Karahıdır Mah. Yolu Üzeri No.:78 Gürsu - BURSA / TÜRKİYE
Tel: (+90) 516 168 61 01 / 850 888 61 00
www.barskimya.com info@barskimya.com