



PROPOLY MASTIC 496

***Polyester Resin Based Two Component
Marble Adhesive Sealant***

PRODUCT DESCRIPTION:

It is a polyester resin based, two component marble adhesive sealant.

FEATURES:

It is resistant to water, moisture and impacts.

It is easily sanded.

It fills the pores.

It has maximum performance.

It is thixotropic.

It has high adhesion strength.

Its adherence is high.

Suitable for top-down ceramic flooring. It can be easily combed.

PRODUCT INFORMATION:

Mastic :

Chemical Base Polyester resin based

Appearance / Color Liquid / cream & beige & white & black

Hardener:

Chemical Base Dibenzoylperoxide paste

Appearance / Color Liquid / White

PERFORMANCE:

(23°C, 50% RH)

Tensile Adhesion 1.34±0.2 N/mm² TS EN 196-1

Density 1.7±0.2 gr/cm³

These values have been obtained as a result of laboratory tests carried out in our company and are valid for the performance of the finished applications at the end of the full drying period.

Values may change due to differences in temperature and humidity values in the construction site environment. Since the temperature and humidity values in the construction site environment and the application surfaces and areas will vary, the values may change.



PROPOLY MASTIC 496

*Polyester Resin Based Two Component
Marble Adhesive Sealant*

USAGE AREAS:

It is used in bonding, repair and filling processes of coating materials such as ceramic, tile, marble, natural stone.

PROPOLY
MASTIC 496
Polyester Resin Based
Two Component
Marble Adhesive Sealant

APPLICATION INSTRUCTIONS:

Surface; It should be cured, dry and solid. It must be cleaned of residues such as oil, grease, dirt, paint, salt vomit that will prevent adhesion. The surface must be rough.

Propoly mastic, approximately 1-3% by weight, 50% dibenzoyl peroxide paste is added and mixed thoroughly with the help of a spatula. Applied . It hardens in 5-8 minutes at 20°C. The adhered surfaces are ready for use 2 hours after the application. Excessive addition of hardener accelerates curing, but may lead to a decrease in bond strength. Do small trials for optimum results.

LIMITATIONS:

Please obey to the application instructions to obtain optimum quality. The application should be done between +5 C and +30 C. It should not be applied in hot, rainy and windy weather. It should not be applied on surfaces where there is a danger of frost. Keep the glue box lid closed after use.

PACKAGING:

Mastic :750 ml tin package

SHELF LIFE:

It is 6 months from the date of production in its original packaging in a moisture-free, dry and cool (temperature between +5 C and +25 C) environment. The lid of the containers should be tightly closed when not in use. It should be kept away from moisture.



PROPOLY MASTIC 496

***Polyester Resin Based Two Component
Marble Adhesive Sealant***

STORAGE CONDITIONS:

It should be stored in its unopened original package, in a moisture-free, dry and cool (temperature between +5 C and +25 C) environment. It should not be left under direct sunlight.

SECURITY:

Do not breathe the product, do not contact the skin and eyes. Use mask. Use protective gloves, goggles and clothing. In case of eye contact, seek medical advice immediately. Make sure that the place is well ventilated during use. Keep out of reach of children. Do not swallow. Keep away from flammable materials. For detailed information and recommendations, please refer to the Safety Data Sheet.

DEKOSTAR San.ve Tic.Ltd. Şti. is not responsible for any application errors that may occur if the product is used for purposes other than its intended use or if the above-mentioned application conditions and recommendations are not followed. Dekostar reserves the right to change its products. Users should consider the latest edition of the Technical Data Sheet of the relevant product.