



PROPLASTER

525

Cement Based Thin Satin Plaster

PRODUCT DESCRIPTION:

It is a thin putty plaster produced for walls and ceilings, used for smoothing interior and exterior plaster surfaces reinforced with white cement and powder polymer.

FEATURES:

It provides high adherence and durability.

It prevents the formation of hairline cracks.

The topcoat contributes to the smooth, solid and uniform appearance of the coating.

PRODUCT INFORMATION:

Chemical Base	Cement-Based
Appearance / Color	Powder / White

PERFORMANCE:

(23°C, 50% RH)

Hollow Unit Volume Mass of Fresh Mortar	1350 ± 200 kg/m ³ TS EN 1015-6
Grain Size Distribution	
Amount remaining on the sieve with 1 mm opening	≤ 1.0% TS EN 1015-1
Application thickness	1-3 mm

These values have been obtained as a result of laboratory tests carried out in our company and are valid for the performance of the finished applications at the end of the full drying period. Since the temperature and humidity values in the construction site environment and the application surfaces and areas will vary, the values may change.

USAGE AREAS:

It is used before painting in order to obtain a smooth surface on cement-based plaster surfaces.

It can be used to create a smooth surface under wallpapers.

APPLICATION INSTRUCTIONS:

Surface; It must be dry, solid and free of dust. It must be cleaned of residues such as oil, grease, dirt, paint, salt vomit that will prevent adhesion.

Slowly pour 25 kg of PROPLASTER onto 6-7 liters of water and mix with the help of a low-speed mixer until no lumps remain. Let the mortar rest for 5-10 minutes to mature. It is mixed again before starting the application.



PROPLASTER

525

Cement Based Thin Satin Plaster

Application Equipment:

Hand Mixer
Steel Trowel

The prepared mortar should be applied to the surface in 1-3 mm thickness. Two coats are recommended for thicker applications. After the first coat is completely dry, the second coat can be applied. For broken, cracked and broken areas on the floor, the mortar should be filled by applying pressure with a steel trowel. After 24 hours, the surface should be moistened with a sponge at regular intervals. Prepared mortar 30 min. should be consumed within the period of use, and the expired mortar should be disposed of.

LIMITATIONS:

Please obey to the application instructions to obtain optimum quality. The application should be done between +5 C and +30 C. It should not be applied in hot, rainy and windy weather. It should not be applied on surfaces where there is a danger of frost. The product should be protected from rain, water, frost and adverse external factors until it cures (28 days).

CONSUMPTION:

1.1 kg/m² for 1mm thickness.

PACKAGING:

In 20 kg kraft bags,
(64 pieces per pallet, 1280 kg)

SHELF LIFE:

It is 1 year from the date of production in its original packaging in dry and non-humid (temperature between +5 C and +25 C) environments. The lid of the containers should be tightly closed when not in use. It should be kept away from moisture.

STORAGE CONDITIONS:

It should be stored in its unopened original package, in a moisture-free, dry and cool (temperature between +5 C and +25 C) environment. It should not be left under direct sunlight.



PROPLASTER

525

Cement Based Thin Satin Plaster

SECURITY:

Since it is cement based, do not breathe the dust, use a mask. Avoid contact with skin and eyes. Use protective gloves, goggles and clothing. In case of eye contact, seek medical advice immediately. Keep out of reach of children. In case of skin contact, wash with plenty of water and soap. Do not swallow. For detailed information and recommendations, please refer to the Safety Data Sheet.

DEKOSTAR San.ve Tic.Ltd. Şti. is not responsible for any application errors that may occur if the product is used for purposes other than its intended use or if the above-mentioned application conditions and recommendations are not followed. Dekostar reserves the right to change its products. Users should consider the latest edition of the Technical Data Sheet of the relevant product.

DEKOSTAR San. ve Tic. Ltd. Şti
Karahıdır Mah. Yolu Üzeri No.:78 Gürsu - BURSA / TÜRKİYE
Tel: (+90) 516 168 61 01 / 850 888 61 00
www.barskimya.com info@barskimya.com